



PRODUCT INFORMATION
Weather Resistance Grade

KOCETAL[®] WR301

Kocetal WR301 is U.V. stabilized grade suitable for outdoor applications

| Property | Test Method | Units | Value |
|--|-------------|-----------------------------|--------------|
| Physical | | | |
| Melt Index | ASTM D1238 | g/10min | 8.0~11.0 |
| Specific Gravity | ASTM D792 | - | 1.41 |
| Water Absorption 23°C, Equilibrium 60%RH | ASTM D570 | % | 0.22 |
| Thermal | | | |
| Melting Point | ASTM D1525 | °C | 166 |
| Heat Deflection Temperature | ASTM D648 | | |
| HDT/A 4.6kg/cm ² (0.45MPa) | | °C | 160 |
| HDT/A 18.6kg/cm ² (1.81MPa) | | °C | 110 |
| Vicat Softening Temperature | ASTM D1525 | °C | 162 |
| Coeff. Of Linear Thermal Expansion | ASTM D696 | x 10 ⁻⁵ cm/cm.°C | 9~11 |
| Flammability | UL 94 | | HB |
| Mechanical | | | |
| Tensile Strength 23°C | ASTM D638 | kg/cm ² (MPa) | 590 (58) |
| Tensile Elongation 23°C | ASTM D638 | % | 40 |
| Flexural Strength 23°C | ASTM D790 | kg/cm ² (MPa) | 800 (78) |
| Flexural Modulus 23°C | ASTM D790 | kg/cm ² (MPa) | 23000 (2256) |
| Notched Izod Impact Strength 23°C | ASTM D256 | kg-cm/cm (J/m) | 5 (49) |
| Rockwell Hardness M scale | ASTM D785 | - | 80 |
| Electrical | | | |
| Surface Resistivity | ASTM D257 | x 10 ¹⁶ Ω | 1 |
| Volume Resistivity | ASTM D257 | x 10 ¹⁴ Ω·m | 1 |
| Dielectric Strength | ASTM D149 | kV/mm | 19 |
| Dielectric Constant 10 ⁶ Hz | ASTM D150 | - | 3.7 |
| Dielectric Dissipation FactorConst: 10 ⁶ Hz | ASTM D150 | - | 0.006 |
| Arc Resistance | ASTM D495 | sec | >200 |

The information provided in this data sheet is based on our present state of knowledge and is estimated by KOLON. This information should not be used as guaranteeing specification limits. KOLON make no warranty and liability in connection with any use of this information.



KTP Industries Inc.

KOLON TOWER, 1-23, BYULYANG-DONG, KWACHEN-CITY KYNG GI-DO, KOREA

Tel. 82-2-3677-3580~9 Fax. 82-2-3677-3558