

Product Data Sheet of SKYGREEN JN200

● Sheet Property (ASTM Method)

Property	Test Method	Unit	Typical Values
Physical			
Specific Gravity	ASTM D792	-	1.23
Mold Shrinkage Parallel to Flow	ASTM D955	%	0.2 – 0.5
Water Absorption (24 hr immersion)	ASTM D570	%	0.13
Rockwell Hardness	ASTM D785	R-scale	105
Mechanical			
Tensile Strength @ Yield 50mm/min (2 inch/min)	ASTM D638	MPa (kgf/cm ²) Psi	45 (460) 6500
Tensile Strength @ Break 50mm/min (2 inch/min)	ASTM D638	MPa (kgf/cm ²) psi	53 (540) 7700
Elongation @ Yield 50mm/min (2 inch/min)	ASTM D638	%	5.0
Elongation @ Break 50mm/min (2 inch/min)	ASTM D638	%	340
Flexural Strength 1.27mm/min (0.05 inch/min)	ASTM D790	MPa (kgf/cm ²) psi	67 (685) 9700
Flexural Modulus 1.27mm/min (0.05 inch/min)	ASTM D790	MPa (kgf/cm ²) psi	1800 (18300) 2.6x10 ⁵
Izod Impact Strength, Notched @ 23 °C(73 °F)	ASTM D256	J/m(kgf · cm/cm) ft · lbf/in	NB
Thermal			
Heat Distortion Temperature @ 0.455 MPa(66 psi)	ASTM D648	°C (°F)	74 (165)
@ 1.82 MPa(264 psi)		°C (°F)	64 (147)
Vicat Softening Temperature @ 1kg load	ASTM D1525	°C (°F)	88 (190)
Optical			
Haze	ASTM D1003	%	< 1.0
Transmittance	ASTM D1003	%	91
Electrical			
Volume Resistivity	ASTM D257	Ohm · cm	10 ¹⁵
Surface Resistivity	ASTM D257	Ohm	10 ¹⁶
Dielectric Constant @ 1kHz	ASTM D150	-	2.8
@ 1MHz			2.6
Dissipation Factor @ 1kHz	ASTM D150	-	0.006
@ 1MHz			0.019
Flammability			
UL Flammability Classification @ min. 3.0 thickness	UL 94	-	HB

- The data listed here is preliminary data sheet of product. Therefore this sheet should not be used to establish specification limits or used alone as a basis for design. This information is not intended as a warranty of any kind. Customers must make their own representative test and assume all risks of use, whether used alone or in combination with other products. SK Chemicals assumes no obligation or liability of any advice furnished by it or results obtained with respect to these products. All warranties of merchantability for a particular purpose or use are excluded and disclaimed.